

EPOXY REÇİNELİ CAM İZOLE BORU FR4



| İÇ ÇAP | DIŞ ÇAP | BOY | €/ADET |
|--------|---------|---------|---------|
| 9 mm | 13 mm | 1000 mm | 11,00 € |
| 11 mm | 15 mm | 1000 mm | 12,00 € |
| 13 mm | 19 mm | 1000 mm | 20,00 € |
| 17 mm | 23 mm | 1000 mm | 21,00 € |
| 19 mm | 25 mm | 1000 mm | 24,50 € |
| 21 mm | 25 mm | 1000 mm | 23,00 € |

POLYGLASS BANT H CLASS



| EN | KALINLIK | BOY | €/Mt. |
|-------|----------|---------|--------|
| 20 mm | 0,30 mm | 200 mt. | 0,28 € |

TEST REPORT

| CUSTOMER | | YATIZ ELEKTRİK LTD.STI., TURKEY | | QF/8.2.4/03 |
|-------------------|---|---------------------------------|---------|-------------|
| TEST REPORT NO. | 5425/ TEST/247 | | | |
| TEST REPORT DATE | 20.07.2007 | | | |
| MATERIAL | POLYGLASS TAPE H-200 | | | |
| QUANTITY | 50,000 POLYGLASS TAPE H-200 MTRS EACH | | | |
| SPECIFICATION NO. | RDSO SPECN. SPEC/E-7/17 OF OCT. 1994 WITH AMENDMENT 1,2 & 3 | | | |
| BATCH NO. | H-67 | | | |
| MFG. DATE | 07/2007 | EXP. DATE | 06/2008 | |
| INVOICE | NO. 247 DATE 20.07.2007 | | | |
| P.O.NO. | BY EMAIL | | | |
| P.O. DATE | 18.06.2007 | | | |

| SL.NO | TEST | UNIT | SPECIFIED | OBTAINED |
|--------------------------------|-----------|------|-------------|-------------------------|
| DIMENSION AND TOLERANCE | | | | |
| 1 | THICKNESS | MM | 0.30 ± 0.05 | 0.300 0.300 0.305 |
| 2 | WIDTH | MM | 20.0 ± 1.5 | 20.5 20.0 20.0 |

CHARACTERISTICS AS SUPPLIED

| | | | | |
|----|--|-------|---|------------------------------------|
| 3 | RESIN CONTENT | % | 27 ± 2 | 27.50 27.45 |
| 4 | NO. OF YARNS PER CM OF WIDTH | NOS | 30 ± 1 | 30 30 |
| 5 | SEALING SOLDER TEST AT 160 °C +/- 2 °C | - | RESIN SHOULD FLOW & STICK WITHIN 1 MINUTE | RESIN FLOW & STICK WITHIN 1 MINUTE |
| 6 | IDENTIFICATION OF RESIN | - | POLYESTER/ ACRYLIC | POLYESTER |
| 7 | KOEFFLER'S SOFTENING POINT OF RESIN | °C | 200 (MAX) | 194 |
| 8 | MASS PER 100 M OF 10 MM WIDE TAPE | KG | 0.56 (APX.) | 0.562 |
| 9 | TENSILE STRENGTH (20 MM WIDTH TAPE) | KG | 500 (MIN) | 555 550 |
| 10 | RECOMMENDED CURING CYCLE (AT 150 °C) | HRS | 5 | 5 |
| 11 | SHELF LIFE BELOW 15 °C | MONTH | 12 | 12 |

CHARACTERISTICS AFTER APPLICATION CURING

| | | | | |
|----|------------------------------|--------|--------------|------------|
| 12 | BREAKING LOAD AT RT | N/MM | 265 (MIN) | 280 285 |
| 13 | ELONGATION AT BREAK AT 20 °C | % | 1.6 (MAX) | 1.53 |
| 14 | ARC RESISTANCE | SECOND | ≥ 120 SECOND | 122 |

Shahabuddin
Q.C. INCHARGE